



# INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCMI] ISSN: 0974-8652

## A review on partial replacement of fine aggregate by tiles in materials

Volume 12, Issue 1 July-Aug: 2016

SK.KHAJA SAMEER ASSISTANT PROFESSOR, DEPT. OF CIVIL ENGINEERING, GDMM COLLEGE  
OF ENGINEERING AND TECHNOLOGY A.P, INDIA

I.CHANDU ASSISTANT PROFESSOR, DEPT.OF CIVIL ENGINEERING, GDMM COLLEGE OF  
ENGINEERING AND TECHNOLOGY A.P, INDIA

*Abstract: This examination manages the effect on the concrete by the partial replacement of fine aggregate by ceramic aggregate. Studies were done on a concrete, with various replacement. The impacts of various replacements 0, 10, 20, 30&40 percent of the waste ceramic tile by weight of concrete with M-30 review. At last, it was reasoned that all the strength qualities (compressive strength, flexural strength & split tensile strength) of concrete increases with the various replacements.*

*Keywords: Compressive Strength, Flexure Strength, Ceramic Waste Tile, Split Tensile Strength.*

### I.INTRODUCTION

Concrete is a most versatile construction material since it is intended to withstand the hazardous situations, with satisfactory strength and durability. Due to overutilization of the concrete material winds up plainly frightened, and furthermore, the generation at bigger rate make numerous perilous to the earth. On opposite side, the waste presented to our condition is an effect to biological cycle, among all mechanical waste, is the significant wellspring of waste which will influence the earth. Cement and aggregate, which are the most basic constituents used in concrete production, are the basic materials required for the construction industry. This certainly incited a constant and extending enthusiasm of natural materials used for their production. Parallel to the necessity for the utilization of the natural resources builds up a creating stress for guaranteeing the earth and a need to spare natural resources, for such as aggregate, by using elective materials that are either reused or discarded as a waste. The utilization of waste items in concrete temperate as well as settles a portion of the transfer issues. Pounded ceramic aggregate can be utilized to deliver the concrete, without influencing strength.

### II. LITRATURE REVIEW

A. M. Sekar (2017) [1] has examined that partial replacement of coarse aggregate by waste ceramic tile in concrete. In this investigation, an endeavor has been made to discover the appropriateness of ceramic coarse aggregate as a conceivable substitute for customary aggregate in concrete. The concrete examples were thrown with blend 1:1.65:2.82 and 1:1.56:2.82. Ceramic waste aggregate 15%, 30%, 45% incomplete replacement, the strength of concrete. The tests were done following 7days and 28 days of the throwing concrete example. The ceramic industry is known to create a lot of calcined-earth wastes every year. So far a colossal part is utilized as a part of landfills. Reusing these losses in concrete could be an inside circumstance. So we lean toward ceramic waste to expand the strength and soundness of concrete.



## INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCMI] ISSN: 0974-8652

B. *Parminder Singh and Dr. Rakesh Kumar Singla (2015) [2]* has considered out that utilization of waste ceramic tiles as coarse aggregate in concrete. The paper provides details regarding the execution of 3 diverse concrete blends containing distinctive proportions of squashed tiles having 20 mm greatest size as coarse aggregate. Conventional Portland Cement 53 review and coarse sand were utilized to create standard concrete blocks. Compressive strength tests were completed on concrete examples at different ages. Test outcomes demonstrate that aside from M 30 blend there is no critical impact on the compressive strength of concrete in M 20 and M 25 stirs up to 20 percent replacement of ordinary 20 mm coarse aggregates with tile aggregates. In any case, past that, strength began diminishing step by step with increment the extent of tile aggregates in concrete.

C. *Ofonime A. Harry and Ifiok E. Ekop (2016) [3]* has looked at that the compressive strength qualities of tile waste concrete. This paper displays the after-effects of an examination concerning the compressive strength attributes of concrete made with ceramic tile waste as coarse aggregates. The level of tile waste fluctuates in ventures of 25% from 0 to 100%. For each considered level of tile wastes, three (3) set of concrete blocks were thrown each for 7, 14 and 28 days curing age which brought about an aggregate of 45 3D squares. The test outcome demonstrated that the compressive strength decreases as the level of tile wastes increments. The 28th-day compressive strength for 25% and 100% replacement were 23.93N/mm<sup>2</sup> and 21.43N/mm<sup>2</sup> separately which is satisfactory for basic lightweight concrete. The particular gravity of tile waste was observed to be 2.27 which is tantamount to the particular gravity of customary aggregate. Slump test additionally demonstrated that workability of concrete reductions with expanding tile waste content.

### III. OBJECTIVE

This work has been done to investigate the properties of fresh and hardened concrete for M-30 grade with the partial replacement of fine aggregate with the waste ceramic tile. In this test compressive strength, split tensile strength, flexural strength, and workability of concrete has been the objective may be summarized as follows:-

- To find out the compressive strength, split tensile strength, and flexural strength of solidified concrete for M30 with the age of 7, 14, 28 and 50 days

### IV. MATERIALS USED & TESTS CONDUCTED

□ The materials used in this work are fine aggregates (stream sand), 10 and 20 mm coarse aggregates which is available locally. Portland-pozzolona cement 43 grade as per IS: 4031-1968 review was utilized all through the test examinations Tests were conducted after partial replacement of fine aggregate with the waste ceramic tile on properties of concrete. The different conducted were as follows:-

# INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCMI] ISSN: 0974-8652

- For Aggregate: -Sieve Analysis, Water Absorption, Specific Gravity, Crushing Value, Impact Strength.
- For Cement: - Cement Consistency, Fineness.

For Concrete: - Workability, Slump Test, Compressive Strength, Flexural Test, Split Tensile Strength

The concrete mix was designed as per IS-10262, 2009 and for designed purpose. We used ACI method and determine the physical properties of the entire gradient such as fine aggregate, coarse aggregate, cement. In the design, we use specific gravity for all gradients such as for coarse aggregate-2.80, fine aggregate-2.65, and for cement -3.15.

**TABLE I: M-30 Mix Proportion used**

Cement	Water	FA	CA	
456	:238.5	: 603	: 1068	[kg/m <sup>3</sup> ]
1	:0.523	: 1.322	: 2.342	

## A. Conventional Concrete and Material Properties

**TABLE II: Properties of Cement**

Type of cement	Initial setting time		Final setting time	
	As per IS	Test time	As per IS	Test time
Portland- pozzolona cement 43 grade	(IS 4031: PART 5)		(IS 4031: PART 5)	
	Minimum	Maximum	Minimum	Maximum
	30 min	55 min	190 min	600 min
		45 min		555 min

*B. Fine Aggregates:* Locally accessible stream sand going through 4.75mm IS Sieve was utilized. The particular gravity of the sand was found as 2.65 and affirming to zone III of table 3.15 of IS 383-1970.

*C. Coarse Aggregate:* Crushed shake aggregate accessible from nearby sources has been utilized. The measure of coarse aggregate was 20mm and 10mm. its particular gravity is 2.65.

*D. Waste Ceramic Tile:* Ceramic waste is accessible from vast ceramic industrial facilities, ceramic item producing units and from regular development exercises. Conventional ceramics, for example, bricks, rooftop and floor tiles, other development materials, and specialized ceramics, for example, porcelain are typically very heterogeneous because of the wide compositional scope of the common muds utilized as crude materials. Around 300 kg of wastes from an Indian ceramic organization (RAK Ceramics Pvt. Ltd., Chennai) was pounded with an altering pole physically to make the ceramic aggregate. In this manner, by utilizing this framework to squash ceramic wastes is conceivable to acquire coarse aggregates, fine aggregates and ceramic powder that subsequent to sieving (IS 4.75 mm strainer) can be utilized without extra work and with insignificant cost suggestions.

# INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCFMI] ISSN: 0974-8652

## V. TESTS CONDUCTED

### A. Consistency of Cement

**TABLE III: Consistency of Cement**

S. No.	Material	Percentage of Replacement				
		0%	5%	10%	15%	20%
1	M20	27	29	31.5	32	33.5
2	M25	28.5	30	32	33.5	34
3	M30	29	31.5	33	33.5	34.5

The usual range of water to cement ratio for normal consistency is between 26% and 34%. The pastes with the partial replacement of ceramic aggregates as fine aggregates showed a consistency mostly similar to normal consistency.

**TABLE IV: Workability of Concrete**

S.No.	% Variation	M30
1	0	75
2	10	60
3	20	52
4	30	45
5	40	34




Fig. 1 Slump Value

From the above outcomes for slump demonstrates that the workability decrements with the expansion in the rates of containing ceramic waste crushed tile aggregate. All explored containing ceramic waste crushed tile aggregate blends had stature slump esteems and worthy workability.

### B. Compressive strength of concrete

**TABLE V: Compressive Strength [N/mm<sup>2</sup>] for M-30**

Compressive strength of M30 (N/mm <sup>2</sup> )					
Days / %	0%	5%	10%	15%	20%
7	28.53	28.43	32.60	33.57	36.53
14	32.50	33.60	36.43	40.03	42.23
28	37.67	39.37	42.47	42.60	45.47
50	42.40	44.50	47.60	45.87	51.53

# INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCMI] ISSN: 0974-8652




Fig.2 Compressive Strength [N/mm<sup>2</sup>] for M-30

From the above table is seen that the compressive strength results represent that concrete casted within M30 grade of concrete at 7, 14, 28 and 50 days have increments with the level of the ceramic waste crushed tile aggregate increment from 0 to 40% at 7, 14, 28 and 50 days.

### C. Flexural Strength

M-30 review of concrete at 28 days, flexural quality is higher than when the level of utilization of 10%, 20%, 30% and 40% of the level of the fired waste smashed tile aggregate with the supplanting of fine aggregate augmentations with the age of 28 days.

TABLE VI: Flexural Strength M-30

Flexure Strength in concrete					
Day's / %	0 %	10 %	20%	30%	40%
28 Days	4.81	4.87	5.10	5.18	5.23




Fig.3 Flexure Strength results of M-30 Grade


# INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCMI] ISSN: 0974-8652

## D. Split Tensile Strength

The Split tensile strength of concrete is expanded when the level of the ceramic waste crushed tile aggregate is increased from 10%, 20%, 30% and 40% usage as a partial replacement in concrete at 28 days in M-30 grade.

**TABLE VII: Split Tensile Strength M-30 Grade**

Tensile Strength in N/mm <sup>2</sup>					
Day's / %	0%	10%	20%	30%	40%
28	4.65	4.98	5.12	5.14	5.28



**Fig. 4 Split Tensile Strength of M30**

The Split tensile strength of concrete is expanded when the level of the ceramic waste crushed tile aggregate is increased from 10%, 20%, 30% and 40% usage as partial replacement in concrete at 28 days in M-30 grade

## CONCLUSION

The Slump exhibits that the workability decrements with the extension in the rates of containing artistic waste smashed tile aggregate with the percentage of 10% to 40%. All investigated containing fired waste pulverized tile aggregate mixes had stature slump regards and commendable workability at M30 grade of concrete. Compressive quality outcomes speak to that concrete threw within M30 review of concrete at 7, 14, 28 and 50 days are enlargements, when the level of the aesthetic waste squashed tile aggregate expansion from 0% to 40% We can see that the flexure quality in M30 audit of concrete at 28 days, flexural quality are higher than when level of usage of 10%, 20%, 30% and 40% of level of the terminated waste crushed tile aggregate with the supplanting of fine aggregate increases with the age of 28 days. We can see that the split tensile strength of concrete is extended when the level of the fired waste squashed tile aggregate have increments from 10%, 20%, 30% and 40% use as an incomplete substitution in concrete at 28 days with the M30 review.



# INTERNATIONAL JOURNAL OF COMPUTATIONAL AND MATHEMATICAL IDEAS [IJCMI] ISSN: 0974-8652

## ACKNOWLEDGEMENT

Thanks to My Guide, management of college and HOD of Civil Engineering Department, Bhopal, (M.P.) for helping me throughout my investigation work.

## REFERENCES

- [1] M. Sekar, "Partial replacement of coarse aggregate by waste ceramic tile in concrete," *international journal for research in applied science & engineering technology (ijraset)*, vol. 5, issue 3, (2017)ic value: 45.98 ISSN: 2321-9653,(2017).
- [2] Parminder Singh and Dr. Rakesh Kumar Singla, "Utilization of Waste Ceramic Tiles as Coarse Aggregate in Concrete," *JMEST*, Vol. 2, Issue 11, ISSN: 3159-0040, November – 2015.
- [3] Ofonime a. harry, "Compressive strength characteristics of tile waste concrete," *international journal of engineering sciences & research technology*, vol 5, issue 8, ISSN: 2277-9655, August-2016.